



# Superior quality, flexible, anti-mold tile grout for joint width up to 12mm

## **Description**

**GROUT CG2** is a high-quality cementitious tile grout that is used for grouting all types of tiles and natural stone. **GROUT CG2** is flexible, making it the ideal choice for indoor or outdoor applications and deformable substrates for joints width of 1-12 mm

**Grout CG2** provides a smooth finish with excellent color stability, abrasion, and mold resistance when used in wet areas such as toilets and kitchens in a vertical or horizontal application.

Grout CG2 is available in 33 standard colors.

#### **Uses**

- Terraces and balconies.
- Wet areas such as toilets, and kitchens.
- Facades.
- Swimming pools.
- Underfloor Heating.
- Commercial and public utility buildings.
- Food packaging area.

## **Characteristics / Advantages**

- Frost resistant.
- Highly flexible.
- Anti-mold.
- High abrasion resistance.
- Color stable.
- Fast return to service.
- Superior adhesion.
- Available in a wide range of colors.

## **Standard Compliance**

BS EN 13888:2009 - CG2WA.

## **Typical Properties**

The following values obtained when tested in accordance with BS EN 13888:2009:

Appearance	Fine powder							
Mixed Density	1.60±0.1 kg/ltr							
Operating time	1-1.5 Hours							
Abrasion resistance (EN13888)	≤ 1000 mm <sup>3</sup>							
Compressive strength @ 28 days (EN13888)	≥ 15 MPa							
Flexural strength @ 28 days (EN13888)	≥ 2.5 MPa							
Shrinkage (EN13888)	≤ 3 mm/m							
Water absorption (EN13888)	After 30min ≤ 2g							
(LIV13000)	After 240min ≤ 5g							
Commissioning Time	24 hours for vertical and horizantal areas							
Time of finishing	15-30 minutes							
Full curing time	7 days							
Service Temperature	-30 to +70 °C							

#### **Application Instructions**

#### Surface preparation

The tile edges and joints should clean from dust, oils, dirt, etc. do not start the grouting unless the tile adhesive is sufficiently set. For tiles and natural stones that are sensitive to color change, a reference sample should be made to ensure suitability.





## Mixing

Pour into a suitable container 6 liters of clean water for each 20 kg **Grout CG2** bag (or 1.5 liters for 5 kg bag or 0.6 liters for 2 kg bag). Add the powder to the water and mix using a low-speed mixing drill fitted with a suitable mixing paddle. Continue mixing for 2-3 minutes until achieving a lumps-free mix. Allow the mixed material to stand for 1-2 minutes, then re-stir slightly with no extra water to be added to the mix.

## **Application**

Apply the mixed material to joint gaps using a rubber base pointing trowel or a hard rubber-ended mop. This process should be performed by fist parallel, then traverse application.

After 15-30 minutes, a fine mortar layer on the surface is cleaned using a damp sponge or cloth. After application, tiles are ready to walk on after 24 hours. Applied grout should not be cleaned by any cleaning agents within 5 days of application. Only clean water is allowed.

## Cleaning

Tools should be cleaned immediately with clean water. Hardened material should be removed mechanically.

## Consumption

Grout consumption depends on the dimensions of the tiles and joint width. Please refer to Appendix A for consumption details.

#### **Packaging**

GROUT CG2 is available in 2, 5 and 20 kg packaging.

#### This product is environmentally friendly

## **Storage**

**GROUT CG2** has a shelf life of 12 months when stored in its original unopened packing in dry conditions. Shelf life may reduce if the recommended storage conditions changed.

#### **Safety Instructions**

Like any cementitious tile adhesive, **GROUT CG2** contains hydraulic cement and may cause irritation to skin or eyes. For further information Refer to the Material Safety Data Sheet.

#### **Disclaimer**

Manaseer Industrial Complex has the right to amend its datasheets anytime. Please make sure to have the latest published datasheet version.





## Appendix A:

Tile Dimensions (mm)		Material Consumption Rate Of Grout CG2 According To Joint Width (kg/m²)												
Length Widt		Thistonese	Joint Width (mm)											
	wiath	Thickness	1	2	3	4	5	6	7	8	9	10	11	12
20	20	3	0.5	1.0	1.4	1.9	2.4	2.9	3.4	3.8	4.3	4.8	5.3	5.8
50	50	6	0.4	0.8	1.2	1.5	1.9	2.3	2.7	3.1	3.5	3.8	4.2	4.6
100	100	6	0.2	0.4	0.6	0.8	1.0	1.2	1.3	1.5	1.7	1.9	2.1	2.3
150	150	6	0.1	0.3	0.4	0.5	0.6	0.8	0.9	1.0	1.2	1.3	1.4	1.5
200	200	7	0.1	0.2	0.3	0.4	0.6	0.7	0.8	0.9	1.0	1.1	1.2	1.3
200	300	7	0.1	0.2	0.3	0.4	0.5	0.6	0.7	0.7	0.8	0.9	1.0	1.1
300	300	8	0.1	0.2	0.3	0.3	0.4	0.5	0.6	0.7	0.8	0.9	0.9	1.0
400	400	10	0.1	0.2	0.2	0.3	0.4	0.5	0.6	0.6	0.7	0.8	0.9	1.0
450	450	10	0.1	0.1	0.2	0.3	0.4	0.4	0.5	0.6	0.6	0.7	0.8	0.9
500	500	10	0.1	0.1	0.2	0.3	0.3	0.4	0.4	0.5	0.6	0.6	0.7	0.8
600	600	10	0.1	0.1	0.2	0.2	0.3	0.3	0.4	0.4	0.5	0.5	0.6	0.6

Note: This coverage is theoretical and may vary due to site wastage and actual joint depth/width.

**Manaseer Industrial Complex** Is a Member of US Green Building







Page 3 of 3

Tel: + 962 6 5800600 Fax: + 962 6 5833890 P.O.Box 141414 Amman 11814, Jordan Website: www.manaseer-ic.com Email: info.shield@Manaseer-ic.com

**Note:** All information provided and recommendations made herein are intended to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use in order to make their own final decision regarding suitability. We do not guarantee results, freedom from patent infringement, or suitability of resultant products for any suggested application with respect to the use of any formula or material described herein.